

Qualche esempio delle miscele maggiormente utilizzate:
 Einige Beispiele der am häufigsten verwendeten Mischungen:
 Quelques exemples de mélanges plus couramment utilisés:
 Some examples of mixtures most commonly used:



Definizione della grandezza Korngrössendefinition Définition de la taille Grain size definition	Dimensioni dei grani Korngrösse Dimension des grains Grain size
Ultrafine - grano, Korn, grain, grain	0.2 - < 0.5 µm
Extrafine - grano, Korn, grain, grain	0.5 - < 0.8 µm
Fine - grano, Korn, grain, grain	0.8 - < 1.3 µm
Medium - grano, Korn, grain, grain	1.3 - < 2.5 µm
Coarse - grano, Korn, grain, grain	2.5 - < 6.0 µm
Extra coarse - grano, Korn, grain, grain	> 6.0 µm

	ISO Grade	HV50		ISO Grade	HV50	
Ultrafine	674	1610 - 1660	Coarse	K50	1000 - 1060	
	Extrafine	K01		1850 - 1950	K60	880 - 940
K10MIK		1760 - 1810		K70	780 - 840	
K15		1555 - 1655		P25F	1475 - 1525	
K15H		1670 - 1730		P35	1360 - 1440	
GX30		1320 - 1360		M1	1400 - 1480	
675		1710 - 1765		M2	1180 - 1250	
Fine	K05	1700 - 1800		Extra coarse	MP3	1160 - 1240
	K10	1650 - 1750				
Medium	K20	1530 - 1630				
	K30	1410 - 1500				
	K40	1255 - 1335				
	P20	1450 - 1550				
	P25	1400 - 1500				
	P30	1350 - 1450				
	P40	1300 - 1400				
	M10	1600 - 1700				
	M20	1520 - 1610				
	Ni	1350 - 1440				